



$\mu'$  ( $\mu''$ )-Frequency



Initial permeability	$\mu_i$	25°C	4000±25%
Saturation magnetic flux density	$B_s$ (mT)	25°C	430
flux density		100°C	270
Remanent flux density	$B_r$ (mT)	25°C	80
		100°C	70

$\tan\delta/\mu_i$	25°C 10kHz	<5
Coerivity	$H_c$ (A/m)	
Relative loss factor		

$\mu_i$ -Temperature



$\tan\delta/\mu_i$ -Frequency

